

EcoRight 50/50 fine stuff

1. Identification

1.1 Introduction

EcoRight 50/50 Fine Stuff is a traditional 1:1 ratio (aggregate to lime) mortar mix using non-hydraulic (fat or pure) lime and, silver sand. Fine Stuff is delivered as a wet mix and is only available in 15 litre tubs.

EcoRight 50/50 Fine Stuff is suitable for repairs to historic buildings as a topcoat/finishing plaster

EcoRight 50/50 Fine Stuff is manufactured using non-hydraulic lime derived from high calcium quicklime (CaO).

1.2 Authority

Materials used conform to the following standards:

Sand	BS EN 13139: 2013
Building Lime	BS EN 459: 2015

EcoRight 50/50 Fine Stuff is a traditional 1:1 ratio (aggregate to lime) mix that is gauged by volume. The aggregates used are a blend of silver and soft sands that produce finely textured mortar that is ideal as a finishing/top coat plaster.

Aggregate grading

To Sieve	% of sand retained
>4mm	0
<4mm >2mm	0
<2mm >1mm	0
<1mm >500µ	5
<500µ >250µ	72
<250µ >125µ	22
<125µ >63µ	0.40
<63µ	0.60
Total	100%

1.3 General Advantages

EcoRight 50/50 Fine Stuff offers several mix advantages:

- Consistent mix proportions.
- Consistent quality of mortar.
- Correct choice of sands.
- Ideal for the repair of historic buildings.
- Can be re-worked up to the point of set.
- Will keep indefinitely as long as the container is air tight and evaporation of moisture does not occur.
- Is pre-mixed so there is little or no need to re-mix or add water.
- Is breathable and enables moisture to evaporate.
- Ideal as a finishing/top coat plaster and for fine joint or gauged brickwork.

2. Description

2.1 Manufacture

Raw materials and end products are subject to regular quality control procedures. The materials are batched by volume.

2.2 Mortar applications

EcoRight 50/50 Fine Stuff is particularly relevant for the repair of historic buildings. This includes as a fine finishing coat for plasterwork

The above is a guide only. If you wish to discuss a specific application in further depth, please call our sales office or speak to an authorised distributor.

2.3 Performance

EcoRight 50/50 Fine Stuff is more flexible than Portland cement-based mortars, which means that expansion joints are not always necessary.

Registered Address: Unit 2 Paddock Road Industrial Estate, Caversham, Reading, Berkshire, RG4 5BY
Tel: 01189 469 153 (head office) +44 (0)845 873 3888 (orders) 01189 946 9176 (fax). Company Reg no: 6561874.

EcoRight Ltd is a member of **The Building Limes Forum**, a charitable organisation which works Internationally to promote research and education and to encourage expertise and understanding in the use of building limes.
© Copyright EcoRight Ltd 2018 ® EcoRight is a registered trade mark



EcoRight 50/50 Fine Stuff is more flexible than gypsum-based plaster and has excellent vapour permeability qualities, which enables the building to “breathe”.

3. Site Work

EcoRight 50/50 Fine Stuff only available in 15 litre tubs.

EcoRight 50/50 Fine Stuff is a pre-mixed wet mortar. Generally, there should be no need for the addition of water to the mix. However, if the mortar is particularly dry then a small amount of water can be added but should be controlled to ensure that the mix does not become saturated.

As the mortar is pre-mixed, only a little additional mixing may be required for it to become fully “workable”. A quick check can be carried out by placing an even spread of plaster onto the reverse side of a trowel. When the trowel is turned over (with the reverse face and mortar facing the ground), the mortar should stick to the underside and not fall away. Additional mixing is best undertaken using a spot board with a spade or hand trowel.

Traditional lime (putty) based mortars and plasters are slow setting due to being temperature and moisture sensitive. Practitioners should not be unduly worried if a “full set” takes weeks to achieve.

If used as a finishing/top coat plaster, **EcoRight 50/50 Fine Stuff** should be applied as a skim not exceeding 2mm. Lime putty-based plasters adhere due to two processes, the first is by mechanical means (e.g. the surface texture of brickwork or preceding plaster coats) and the second is by suction. If suction is not controlled and the plaster surface at the interface with the background is allowed to dry too quickly, adhesion will be lost and the plaster will fall away.

Before application, backgrounds should be dampened down using a mist spray this includes brickwork and preceding plaster coats. The surface should be damp without the formation of beads of water on surfaces. Once

the plaster has been applied, control the drying process by damping down with a fine mist spray. Through controlling the suction and drying the longevity of the plaster is greatly increased.

Protection should be given against frost, wind, rain and direct sunlight during the early setting period – hessian and/or plastic sheeting may be required.

The application of artificial background heat to increase setting times is discouraged, unless at low temperatures (between 10-14°C) as quick drying will cause problems as outlined in the previous paragraph

4. Coverage (approximations only)

Fine Stuff	Finishing/Top Coat Plaster (3mm)
25kg	3.75m ²
½ tonne	75m ²
1 tonne	150m ²

5. Health and Safety

Lime based mortars are classified as an irritant and are alkaline in nature (see Health and Safety Datasheet for more details).

Registered Address: Unit 2 Paddock Road Industrial Estate, Caversham, Reading, Berkshire, RG4 5BY
Tel: 01189 469 153 (head office) +44 (0)845 873 3888 (orders) 01189 946 9176 (fax). Company Reg no: 6561874.

EcoRight Ltd is a member of **The Building Limes Forum**, a charitable organisation which works Internationally to promote research and education and to encourage expertise and understanding in the use of building limes.
© Copyright EcoRight Ltd 2018 ® EcoRight is a registered trade mark

